


Protective gloves that are certified in accordance with the extended test methods of EN 388:2016 are marked as follows:



	0	1	2	3	4	5
Abrasion resistance <i>Rotations</i>	0 – 99	100 – 499	500 – 1,999	2,000 – 7,999	8,000 +	
Cut resistance <i>(Coupe test) - Index</i>	0 – 1.1	1.2 – 2.4	2.5 – 4.9	5 – 9.9	10 – 19.9	20 +
Tear resistance <i>Newtons</i>	0 – 9.9	10 – 24.9	25 – 49.9	50 – 74.9	75 +	
Puncture resistance <i>Newtons</i>	0 – 19.9	20 – 59.9	60 – 99.9	100 – 149.9	150 +	
Cut resistance <i>(TDM test) Newtons</i>	A (≥2)	B (≥5)	C (≥10)	D (≥15)	E (≥22)	F (≥30)