

Technical Data - Tubolit AR Fonoblok

Brief description	Flexible, closed-cell extruded insulation material to reduce noise and prevent condensation especially on cast iron pipes for waste water, rain water and sewage pipes.
Material type	Foam material based on polyethylene. Factory made polyethylene foam (PEF) according to EN 14313.
Colour	blue
Material Special Information	Self-adhesive coating on tapes: pressure-sensitive adhesive coating on modified acrylate basis with mesh structure, covered with polyethylene foil.
Applications	Acoustical and thermal insulation of internal waste water, rain water and sewage pipes in residential and non-residential buildings. For complex and large diameter rain collecting and (roof-) drainage pipes, to provide optimal protection against the risk of condensation, we recommend using Armaflex insulation.
Remarks	Declaration of Performance is available in accordance with Article 7(3) of Regulation (EU) No 305/2011 on our homepage: www.armacell.com/DoP

Property	Value/Assessment				Test ^{*1}	Special Remark	
Temperature Range							
Temperature Range	max. service temperature		+ 100 °C		(+ 85 °C for tapes)	EU 5677 EU 5682	Tested acc. to EN 14707 and EN 14313
	min. service temperature				(as is usual in plumbing installations)		
Thermal Conductivity							
Thermal Conductivity ¹	ϑ_m 40		[°C]		$\lambda =$	EU 5677 EU 5682	Declared acc. to EN ISO 13787 Tested acc. to EN ISO 8497
	Tubolit AR Fonoblok	$\lambda \leq 0,045$	W/(m · K)		$[41 + 0,1 \cdot \vartheta_m + 0,0008 \cdot$ $(\vartheta_m - 40)^2]/1000$		
	Tubolit AR tape	$\lambda \leq 0,045$	W/(m · K)		$[41 + 0,1 \cdot \vartheta_m + 0,0008 \cdot$ $(\vartheta_m - 40)^2]/1000$		
Fire performance							
Reaction to fire ²	Tubolit AR Fonoblok		E			EU 5677 EU 5682	Classified acc. to EN 13501-1
	Tubolit AR tape		E				Tested acc. to EN ISO 11925-2
Acoustic Performance							
Reduction of structure-borne sound transmission	on cast-iron waste water pipes		≤ 15 dB(A)			D 2144	Tested acc. to EN 14366
Other technical features							
Dimensions and tolerances	In accordance with EN 14313, table 1 and 2					EU 5677 EU 5682	Tested acc. to EN 822 EN 823 EN 13467
Storage & Shelf life	Tapes self-adhesive: 1 year						Can be stored in dry, clean rooms at normal relative humidity (50% to 70%) and ambient temperature (0 °C – 35 °C).

1. Due to testing method and laboratory equipment, thermal conductivity is measured for Tubolit DG, S and DHS in a regular way

2. The reaction to fire classification is valid on metal surfaces.

*1 Further documents such as test certificates, approvals and the like can be requested using the registration number given.

All data and technical information are based on results achieved under typical application conditions. Recipients of this information should, in their own interest and responsibility, clarify with us in due time whether or not the data and information apply to the intended application area. During storage of the product blooming on the surfaces may occur, especially at wall thickness below 19mm. This blooming does not affect the technical properties of the material, but can affect the adhesion properties. Therefore, the surface needs to be cleaned (wiped off) before adhesives can be applied.